

## TEST REPORT

Your ref : 41718  
Our ref : FPE/46171/19  
Enquiries : J Maswikaneng  
Tel no : 012 428 6010  
Report : BTC-190918-00042  
Page : 1 of 2  
Date : 2019/09/18

SHOPSPEC LIGHT STEEL FRAME BUILDERS  
Attention: Lucre Deale  
PO Box 11037  
Pietermaritzburg  
3206

### FIRE TETSING OF MATERIAL, COMPONENTS AND ELEMENTS USED IN BUILDINGS PART 5 - NON COMBUSTABILITY TEST AT 750 °C OF BUILDING MATERIALS SANS 10177 Part 5: 2012

#### 1. SIGNIFICANCE OF THE TEST RESULTS CONTAINED IN THIS REPORT

- 1.1 Refer to the print at the back of this page.
- 1.2 The sample described was tested in accordance with SANS 10177-5 "Non combustibility test at 750°C of building materials".

#### 2. CONCLUSION

The sample was found to be combustible and is thus classified as B. The UoM was applied to the result and the outcome remains the same.

#### 3. DESCRIPTION OF SAMPLE

One sample of thermally insulated panel/board material was received. The sample consisted of three sheets each being ±300 mm long, ±300 mm wide with a thickness of ±16 mm. The boards consisted of PU foam insulation with a white steel facing on the one side and foil facing on the other. The date of manufacture, conditioning and sampling history prior to receipt of the sample is unknown.

Date of receipt: 2019/08/12  
Date of test: 2019/09/18  
Name of manufacturer: Spänl  
Product trade name: Mono Flat  
Measured density of material: 167 kg/m<sup>3</sup>

#### 4. CONDITION OF SAMPLE.

The sample was found to be in a suitable condition for testing.

1 Dr Lategan Road, Groenkloof, Private Bag X191, Pretoria, 0001.  
Tel +27 12 428 7911. Fax +27 12 344 1568

SABS Commercial SOC Ltd conducted a conformity assessment pertaining to a sample of the product, commodity or system identified and the outcome recorded in this test report only relates to that specified sample. The conformity assessment outcomes recorded in the test report do not imply SABS Approval of the quality and/or performance of the sample(s) in question and the test results do not apply to any similar sample that has not been tested. (Refer also to the conditions of test printed on the back of this page.) This report may not be reproduced except in full. The authenticity of this report and its contents can be confirmed by contacting the person who signed it.

The acceptance of a sample for test and the issue of a test report are subject to SABS' Conditions of Test, which are the following:

1. If published or reproduced by the client, a test report shall be reproduced in full i.e. the reproductions shall contain the printed as well as the typed parts of the report, nothing excerpted.
2. A test report relates only to a sample submitted for the actual test. It furnishes or implies no guarantee whatsoever in respect of a similar sample that has not been tested by the SABS.
3. This test report does not imply that the user has obtained pre-approval to apply the SABS certification mark nor does it imply approval by SABS, of the quality and/or performance of the sample that has been tested. No person may falsely claim or declare that any commodity, product or service complies with a South African National Standard or other publication of the SABS.
4. While every endeavour will be made to ensure that a test is representative and accurately performed, and that a report is accurate in the quoted results and conclusions drawn from the test, in terms of the Standards Act, SABS or its officers shall not be liable for anything done or omitted in good faith when error made in carrying a test.

**5. CONDITIONING OF THE SAMPLE**

The sample was conditioned in a ventilated oven at  $60 \pm 7,5$  °C for 20 h and cooled to ambient temperature in a desiccator before the test.

**6. NATURE AND METHOD OF TEST**

The tests to establish the combustibility of the sample of material were carried out in accordance with the requirements of SANS 10177 - 5:2012 Non-Combustibility at 750°C of building materials".

**7. EQUIPMENT INFORMATION**

7.1	Tube furnace	: Verified
7.2	Digital thermometer	: Calibrated AVC-180702-00023
7.3	Thermocouples	: Calibrated AVC-180702-00023
7.4	Scale	: Calibrated 2018/B051
7.5	Stopwatch	: Calibrated 94318
7.6	Conditioning oven	: Calibrated 730763(temp) 103855(%RH)
7.7	Measuring tape	: Calibrated 17-4585

**8. RESULTS**

Nature of test	Result				Requirement
Non-Combustibility	Specimen 1	44 seconds			If observed to flame continuously for 10s or more classify as combustible.
	Specimen 2	46 seconds			
	Specimen 3	47 seconds			
	Furnace temperature	Initial (°C)	highest (°C)	Temperature rise (°C)	If furnace temperature rises more than 50 °C from initial temperature classify as combustible
	Specimen 1	747,8	793,0	45,2	
	Specimen 2	754,3	797,9	43,6	
	Specimen 3	753,4	798,6	45,2	

The sample was found to be combustible (B).



A van der Walt  
TEST OFFICER: FIRE PROTECTION ENGINEERING



J Maswikaneng  
MANAGER: CIVIL LABORATORIES

< END OF REPORT >

This report relates only to the specific sample(s) tested as identified herein. It does not imply SABS approval of the quality and/or performance of the item(s) in question and the test results do not apply to any similar item that has not been tested.  
(Refer also the complete conditions printed on the back of the official test report)